

TECHNICAL DATA SHEET

Fortis COAT 519 SATIN – Moisture curing non-yellowing clear polyurethane

ISSUED: December 2014

INTRODUCTION

FORTIS COAT 519 SATIN – Moisture curing non-yellowing clear polyurethane

Is a high performance moisture curing, aliphatic (non-yellowing) clear polyurethane finish coat for wood, especially wooden floors, ground cementitious surfaces and for some of the Fortis range of floor systems. It is suitable for brush, roller or spray application. Please note this product is also available in Gloss & Matt.

USE

Suitable for interior and exterior use.

FEATURES

Non-yellowing, moisture curing polyurethane finish
 Contains protective UV absorbers
 Fast curing in a wide temperature range
 Tyre stain resistant
 Low odour (xylene free) in comparison to alternative products

TECHNICAL DATA

| | |
|-----------------|---|
| Colour | Clear |
| Pack Size | 4lt and 20lt gloss only |
| Film Thickness | 50µm @ 8m ² /litre |
| Coverage Rate | 8-10m ² per litre for flooring, 12-15m ² per litre for vertical applications |
| Final Cure | 7 days |
| Recoat Time | 6-12 hours depending on temperature and ventilation. It is essential to sand between coats after 12 hours cure for improved inter-coat adhesion. |
| Number of coats | The SATIN should be used as a final coat after the Fortis Coat 519 GLOSS has been used as build coats. Two coats of GLOSS and one coat of SATIN are sufficient unless bare timber has been exposed. |
| Clean up | Use only Fortis Polyurethane Brush Cleaner |
| Shelf Life | 12 months unopened, store in cool, dry conditions. |

APPLICATION

SURFACE PREPARATION

Substrates should be thoroughly sanded or ground to provide a keyed surface, and existing coatings tested for solvent resistance. Remove all contaminants. Concrete surfaces should be cleaned/etched with Fortis CCA or diamond ground and primed with Polyurethane Adhesion Promoter Refer to 'Application' advice below

APPLICATION

Decant sufficient for immediate use into a roller tray or working pot. Seal original container to prevent moisture exposure. Decant only the amount that is sufficient for 30 minutes use and **do not** return unused product to original container. Apply by floor brush or mohair roller. Sand lightly between coats to remove defects. In cold conditions add up to 2% Fortis Through-cure Catalyst Solution to achieve normal application viscosity and cure rate. Thin as required for block or paver penetration coat with Fortis Reducer. Use appropriate PPE if applying by spraying.

TECHNICAL DATA SHEET

NUMBER OF COATS

The SATIN should be used as a final coat after the Fortis Coat 519 GLOSS has been used as build coats. Two coats of GLOSS and one coat of SATIN are sufficient unless bare timber has been exposed. It is essential to sand between coats after 12 hours cure for improved inter-coat adhesion. Final cure is achieved after 7 days.

CLEAN UP

Use only Fortis Polyurethane Brush Cleaner.

SAFETY

Contains isocyanates. When sprayed, this product may be harmful by inhalation. Do not breathe vapour or spray. Avoid contact with skin and eyes. Wear suitable protective clothing, gloves, eye and face protection, including suitable breathing protection, such as an air-supplied respirator or hood. Avoid contact with exposed skin. Please refer to Material Safety Data Sheet for further information.

Disclaimer

Fortis products should be used in accordance with the information contained here. Each user should read and consider this information carefully in the context of how the products will be handled and used in the workplace including in conjunction with other products. While the information contained here is to the best of our knowledge at the date of publication, Fortis makes no representation about the accuracy of the information. If you need clarification or more information, you should contact Fortis Adhesives & Coatings office directly. Fortis products are sold without express or implied warranties, other than as provided by statute, and subject to our standard terms and conditions (provided to customers and available on request). Subject to our standard terms and conditions, and any statutory provisions, Fortis accepts no responsibility (including in negligence) for loss or damage of any nature resulting from the use of Fortis Adhesives & Coatings products or reliance upon the information contained here