

TECHNICAL DATA SHEET

Fortis AD5105-S – Timber construction Adhesive

ISSUED: July 2015

INTRODUCTION

FORTIS AD5105-S

Timber construction adhesive (Meets EN302 /AS/NZS 4364:2010) GLTAA CERTIFICATE # 007

Is a single component, moisture curing, high strength, polyurethane timber finger joining and laminating adhesive. It reacts rapidly, in as little as 5 minutes, with atmospheric moisture, to provide a superior bond for load bearing timber applications.

USE

Fortis AD5105_S Timber construction Adhesive provides superior bonding. Compliant with **EN302**, it can be used as an adhesive for **load bearing timber structures**. Furthermore, it has been certified according to **AS/NZS 4364:2010** and is approved for the use in the load bearing engineered wood products for structural laminating applications. It is water resistant making it excellent for jobs requiring extra durability and can be used for both interior and exterior applications.

FEATURES

Provides excellent adhesion even at very low spread rates.
Reacts rapidly in as little as 2-5 minutes

TECHNICAL DATA

Appearance	Opaque/green liquid
Coverage rate	55 – 110 gsm subject to substrate
Working time	3-9 minutes
Cure time	15 – 20 minutes
Clean Up	Wet: Solvent Dry: Mechanically
Pack Size	225
Shelf life	12 months unopened, store in cool, dry conditions.

APPLICATION

SURFACE PREPARATION

- Excellent wood-to-wood contact is necessary to achieve optimum bond strength. A smooth surface achieved through planing or similar technique will aid in providing a good wood-to-wood contact. A good mechanical fit for finger-jointing is necessary and interanal or bonding pressures for laminating must be at least 1400kPa for optimum performance
- Extensive laboratory experiments have shown that to achieve optimum performance with the **FORTIS AD5105-S** a water mist must be applied to the wood. The water mist applied prior to glue application, **“TO BOTH ADHERING SURFACES”**. The water application should be approximately 30-50 gsm for both adhering faces. (this process has been found beneficial for the oiliest of Australian Timbers)

APPLICATION

- Through Finger jointing combs or special application bars. Small areas can be brush applied
- With the use of a water mist, **FORTIS AD5105-S** is not drastically affected by the moisture content of the wood. Assembly time tolerances will be mill and substrate specific. However, a good rule of thumb for minimum assembly time tolerances with the recommended water misting is 2-3 minutes total assembly time.
- **FORTIS AD5105-S** can be heated up to 35°C prior to pumping in order to reduce the apparent viscosity and improve pumping ability and flow. (Ask Fortis for simple setup of heat rooms)
- The cure time of **FORTIS AD5105-S** can be accelerated with heat and consequently retarded with colder temperatures. Heating of the substrate, glueline or adhesive itself can accelerate cure.
- **FORTIS AD5105-S** generally requires lower dosages than traditional resins used for engineered wood products. Typically dosages of 55 – 110 grams per square meter (gsm) are common. Assembly time tolerances with **FORTIS**

AD5105-S are dependent on the wood moisture content, spread rate, temperature of the substrate, temperature and relative humidity of the mill and atmospheric conditions, etc.

- As previously mentioned an excellent wood-to-wood contact is necessary to achieve optimum bond strength. If products have not been under pressure for the full time to a testable bond (as in finger - jointing applications), it is important that the finished products are handled gently until a testable bond has been achieved.

CLEAN UP

Clean up whilst adhesive is still fluid using methylated spirits. If adhesive has dried clean up mechanically.

PLEASE NOTE: Never attempt to clean-up or flush a system of **FORTIS AD5105-S** adhesive with water as it will only accelerate cure.

For technical support on setup, machinery, pumps types please contact the team at Fortis Adhesives and Coatings.

SAFETY

- KEEP OUT OF REACH FROM CHILDREN
- DO NOT spray directly on humans or pets
- DO NOT spray on or near naked flame, pilot light, heat or incandescent material
- Avoid contact with eyes and skin and avoid breathing the vapour or spray mist.
- Store in cool, dry conditions, out of direct sunlight and in a well ventilated area. DO NOT store below 10°C or over 50°C.
- Good industrial hygiene should be observed at all times – Appropriate PPE should be worn including impervious gloves & eye wear.

For further information, refer to the Fortis Material Safety Data Sheet. www.fortisadhesives.com.au

Disclaimer

Fortis products should be used in accordance with the information contained here. Each user should read and consider this information carefully in the context of how the products will be handled and used in the workplace including in conjunction with other products. While the information contained here is to the best of our knowledge at the date of publication, Fortis makes no representation about the accuracy of the information. If you need clarification or more information, you should contact Fortis Adhesives & Coatings office directly. Fortis products are sold without express or implied warranties, other than as provided by statute, and subject to our standard terms and conditions (provided to customers and available on request). Subject to our standard terms and conditions, and any statutory provisions, Fortis accepts no responsibility (including in negligence) for loss or damage of any nature resulting from the use of Fortis Adhesives & Coatings products or reliance upon the information contained here